

BURNS DOANEBURNS DOANE SWECKER & MATHIS LLP
ATTORNEYS AT LAWALEXANDRIA, VIRGINIA
REDWOOD SHORES, CALIFORNIA
DURHAM, NORTH CAROLINA**REPLY TO:**

P.O. Box 1404

Alexandria, Virginia 22313-1404

TELEPHONE: +1.703.836.6620**FACSIMILE:** +1.703.836.2021 (Group 3)
+1.703.836.0028 (Group 4)**DATE:** October 1, 2003

RECIPIENT INFORMATION	SENDER INFORMATION
To: Exr. Karabi Guhary	From: Scott W. Cummings
Voice Tel. No.: 703-305-1971	Voice Tel. No.: 703-836-6620
Fax Tel. No.: 703-305-1971 703-746-4822	Sent By: geh
Your Ref.: 09/817,164	Our Ref.: 032566-010
	Total Pages (Incl. Cover Page): 4

RE: PROPOSED AGENDA FOR OCT. 2, 2003 INTERVIEW**MESSAGE:**

Exr. Guhary:

Attached is a proposed agenda for tomorrow's interview.

Best regards,
Scott Cummings*Interview*

NOTE: The information contained in this facsimile message is attorney-client privileged and contains confidential information intended only for the use of the person(s) named above and those expressly authorized to receive it. If you are not the intended recipient, you are hereby notified that any dissemination, distribution or copying of this message is prohibited and you are asked to notify us immediately by telephone and to return this message to us by mail without copying it.

Any questions regarding compatibility should be directed to our Office Services Department at +1.703.836.8620.

Received from <703 836 2021> at 10/1/03 2:34:23 PM [Eastern Daylight Time]

(BDSM 05/01)

PROPOSED - NOT FOR ENTRY IN THE OFFICIAL RECORD**PROPOSED AGENDA FOR OCTOBER 2, 2003 PERSONAL INTERVIEW****I. PROPOSED DRAWING AMENDMENT**

A new figure 9 (attached) is proposed to address the drawing objection. It is believed that new figure 9 provides clear support for the features of claims 34 and 36-38, without introducing any new matter.

II. PRIOR ART REJECTIONS - EVIDENCE OF DISTINCTIONS BETWEEN PRIOR ART AND CLAIMED NANOTUBES**(A) Hsu Reference**

Evidence has been collected demonstrating the fundamental **structural** distinctions between the coating of "pre-formed" nanotubes of the present application and the *in situ* grown nanotube coating of the prior art.

Below is a micrograph illustrating the random and bundled nature of a coating formed from pre-formed nanotubes. When compared to the illustrations of Hsu, which show the aligned and ordered nature of the CVD grown nanotube coating of Hsu, the difference is clear.



Further physical distinctions include: the coating of Hsu requires a catalyst layer while the coating of the invention does not, nanotubes grown by CVD as in Hsu tend to be multiwalled, the pre-formed nanotube coating of the invention can comprise single-walled nanotubes.

(B) Gartner reference

Gartner fails to disclose or teach coating of any type of nanotubes, much less the coating of pre-formed nanotubes as required by the present invention.

PROPOSED - NOT FOR ENTRY IN THE OFFICIAL RECORD

Contrary to the grounds of rejection, the choice of nanotubes vs. nanoparticles does in fact provide a technical advantage over the nanoparticles of Gartner.

For example, when considering the property of field emission, nanotubes provide superior performance and capabilities when compared to particles. The higher aspect ratio (length/width) of nanotubes provides enhanced emission properties compared to Gartner's particles.

Below is emission data reported for nanotubes. Evidence of the superiority of nanotubes }
is evident when compared to Figure 1 of Gartner.

Table 1. Emission characteristics of SWNT films formed by EPD and other techniques. The measurement was done using a constant DC voltage. The threshold field is defined as the electrical field required for the emission current density to reach 0.01 mA/cm². The current decay is calculated by $(I_{\text{initial}} - I_{\text{final}}) / I_{\text{initial}}$, where I_{initial} is the initial emission current and I_{final} is the emission current after 10 h of measurement.

Materials	Threshold field [V/ μm]	Initial emission current density [mA/cm ²]	Emission current decay after 10 hours [%]
As-grown SWNT mat	1.3	200	50
Purified SWNT paper (made by filtration)	1.0	93	40
CVD SWNT film [a]	3.1	10	79
EPD long SWNT film	1.4	83	28

[a] Dr. Jie Liu et al., unpublished results.